

SPEED-E LASER

WOODFREE OFFSET PAPER



Mill
MM Kwidzyn, Poland

1. Technical specifications

Parameter	Measurement				Unit	Standard
Substance	70 ± 2	75 ± 2	80 ± 2	90 ± 2	g/m ²	EN ISO 536
Moisture content	4,0 - 5,5	4,0 - 5,5	4,0 - 5,5	4,0 - 5,5	%	EN ISO 287
Thickness	87 ± 3	94 ± 3	100 ± 3	112 ± 3	µm	ISO 534
Whiteness	146 ± 3	146 ± 3	146 ± 3	146 ± 3	CIE	ISO 11475
Opacity	90 ± 2	92 ± 2	93 ± 2	95 ± 2	%	ISO 2471
Bendtsen roughness	150 ± 50	150 ± 50	150 ± 50	150 ± 50	cm ³ /min	ISO 8791-2
Cobb ₆₀	30	30	30	30	g/m ²	EN ISO 535

2. Certificates



Please collect used paper for recycling

- 100% ECF Fibres