

SPEED-E NOTE*

WOODFREE OFFSET PAPER



Mill
MM Kwidzyn, Poland

1. Technical specifications

Parameter	Measurement	Unit	Standard
Substance	90 ± 3	g/m ²	EN ISO 536
Moisture content	5,5 ± 1	%	EN ISO 287
Thickness	108 ± 3	µm	ISO 534
Whiteness	166 ± 2	CIE	ISO 11475
Opacity	95 ± 2	%	ISO 2471
Bendtsen roughness	150 ± 50	cm ³ /min	ISO 8791-2
Cobb ₆₀	25 ± 5	g/m ²	EN ISO 535

2. Certificates



Please collect used paper for recycling

- 100% ECF Fibres