

SPEED-E PREPRINT

WOODFREE OFFSET PAPER



Mill
MM Kwidzyn, Poland

1. Technical specifications

Parameter	Measurement			Unit	Standard
Substance	75* ± 2	80 ± 2	90 ± 2	g/m ²	EN ISO 536
Moisture content	3,8 - 5,2	3,8 - 5,2	3,8 - 5,2	%	EN ISO 287
Thickness	100 ± 3	106 ± 3	116 ± 3	µm	ISO 534
Whiteness	166 ± 2	166 ± 2	166 ± 2	CIE	ISO 11475
Opacity	93 +2/-1	94 +2/-1	95 +2/-1	%	ISO 2471
Bendtsen roughness	180 ± 50	180 ± 50	180 ± 50	cm ³ /min	ISO 8791-2
Cobb ₆₀	30	30	30	g/m ²	EN ISO 535

2. Certificates



Please collect used paper for recycling

- 100% ECF Fibres